Sinokem Industry Co., Limited

Add:Unit 04, 7/F, bright way tower NO. 33 mong kok road, kowloon,HK Tel/Fax: 0086-29-83331293

Tel/Fax: 0086-29-83331293 Email:sales@sinokem.com Website: www.sinokem.com



TECHNICAL DATA SHEET

MHEC MH200000

Product Description:

CAS No: 9032-42-2

Sinocel MHEC MH200000 is designed to enhance the quality and processing characteristics of cement-based materials such as cement-based tile adhesives and . Compatible with all conventional mineral and organic binders, Sinocel MHEC MH200000 adds excellent open time, slip resistance, impact resistance, adhesion and shear strength. It also enhances workability and water retention.

Typical applications

Skim coat/wall putty
Dry mix

Performance advantages

open time
slip resistance
quick, lump-free dissolution
excellent adhesion and shear strength
compatible with all conventional mineral and organic binders
easy workability
optimum consistency
low stickiness
high yield

Product Specification

Physical form	White powder
Moisture	Max.6%
РН	4.0-8.0
Viscosity	
Brookfield LV, 2% solution (20°C) Brookfield RV, 2% solution (20°C)	160000-240000mPa.s 75000-85000mPa.s

Sinocell, Best choice for you

Sinokem Industry Co.,Limited

Add:Unit 04, 7/F, bright way tower NO. 33 mong kok road, kowloon,HK Tel/Fax: 0086-29-83331293 Email:sales@sinokem.com Website: www.sinokem.com



Packing:

Sinocel is supplied in multi-ply paper bags with polyethylene intermediate layer, containing 25 kgs; shrink palletizing is available by ordering a minimum quantity of 600 kgs.

Storage and Shelf Life

Sinocel should be stored in a cool and dry place and protected against moisture. Since the product is thermoplastic. the storage temperature not over 30 Deg.C. It should not be subjected to pressure of high temperatures during storage because of the risk of caking. Storage time should not exceed three years from receipt of delivery. If you can't use out one bag on time, you'd better seal it again.