

Sinokem Industry Co., Limited

Add: Unit 04, 7/F, Bright Way Tower NO. 33
Mong Kok Road, Kowloon, HK
Tel/Fax: 0086-29-83331293
Email: sales@sinokem.com
Website: www.sinokem.com



TECHNICAL DATA SHEET

MHEC MH30000

Product Description :

CAS No : 9032-42-2

Sinocel MHEC MH30000 is designed to enhance the quality and processing characteristics of cement-based materials such as cement-based tile adhesives and . Compatible with all conventional mineral and organic binders, Sinocel MHEC MH30000 adds excellent open time, slip resistance, impact resistance, adhesion and shear strength. It also enhances workability and water retention.

Typical applications

Skim coat/wall putty

Dry mix

Performance advantages

open time

slip resistance

quick, lump-free dissolution

excellent adhesion and shear strength

compatible with all conventional mineral and organic binders

easy workability

optimum consistency

low stickiness

high yield

Product Specification

| | |
|-----------------------------------|------------------|
| Physical form | White powder |
| Moisture | Max.6% |
| PH | 4.0-8.0 |
| Viscosity | |
| Brookfield LV, 2% solution (20°C) | 24000-36000mPa.s |
| Brookfield RV, 2% solution (20°C) | 15000-20000mPa.s |

Sinocell, Best choice for you

Sinokem Industry Co., Limited

Add: Unit 04, 7/F, Bright Way Tower NO. 33
Mong Kok Road, Kowloon, HK
Tel/Fax: 0086-29-83331293
Email: sales@sinokem.com
Website: www.sinokem.com



Packing:

Sinocel is supplied in multi-ply paper bags with polyethylene intermediate layer, containing 25 kgs; shrink palletizing is available by ordering a minimum quantity of 600 kgs.

Storage and Shelf Life

Sinocel should be stored in a cool and dry place and protected against moisture. Since the product is thermoplastic, the storage temperature not over 30 Deg.C. It should not be subjected to pressure of high temperatures during storage because of the risk of caking. Storage time should not exceed three years from receipt of delivery. If you can't use out one bag on time, you'd better seal it again.